

**ABSTRACT OF THE DISCLOSURE**

STI divot formation is eliminated or substantially reduced by employing a very thin nitride polish stop layer, e.g., no thicker than 400Å. The very thin nitride polish stop layer is retained in place during subsequent masking, implanting and cleaning steps to form dopant regions, and is removed prior to gate oxide and gate electrode formation.